

## AMENDMENTS TO THE CLAIMS

This listing of claims will replace all prior versions, and listings, of claims in this Application:

1) (ORIGINAL) A composition of matter useful as a phosphor in light emitting diodes, which comprises a material described by the formula:



in which:

M comprises one or more elements selected from the group consisting of: Be, Mg, Ca, Sr, Ba, Zn;

A comprises one or more elements selected from the group consisting of: Al, Ga, In, Y, La, and Gd;

B comprises one or more elements selected from the group consisting of: Eu, Ce, Cu, Ag, Al, Tb, Cl, Br, F, I, Mg, Pr, K, Na, and Mn,

wherein B is present in any amount between 0.0001% and about 10 % in mole percent based on the total molar weight of said composition, and wherein x and y are each independently any value between 0 and 1, subject to the proviso that the sum of x and y is equal to any number in the range of between about 0.75 and about 1.25.

2) (CURRENTLY AMENDED) A composition according to claim 1 wherein  $[[ 0 \leq x \leq 1 \text{ and } 0 \leq y \leq 1 ]]$   $0 < x < 1 \text{ and } 0 < y < 1$ .

3) (CURRENTLY AMENDED) A composition according to claim 1 wherein  $[[ 0.5 \leq x \leq 1 \text{ and } 0 \leq y \leq 0.5 ]]$   $0.5 \leq x < 1 \text{ and } 0 < y \leq 0.5$  .

4) (CURRENTLY AMENDED) A composition according to claim 1 wherein  $[[ 0 \leq x \leq 0.5 \text{ and } 0 \leq y \leq 0.5 ]]$   $0 < x \leq 0.5 \text{ and } 0 < y \leq 0.5$  .

5) (CURRENTLY AMENDED) A composition according to claim 1 wherein  $[[ 0 \leq x \leq 0.5 \text{ and } 0.5 \leq y \leq 1.0 ]]$   $0 < x \leq 0.5 \text{ and } 0.5 \leq y < 1.0$ .

6) (CURRENTLY AMENDED) A composition according to claim 1 wherein x is greater than about 0, and y is about 1.

7) (CURRENTLY AMENDED) A composition according to claim 1 wherein x is about 1, and y is greater than about 0.

8) (ORIGINAL) A composition according to claim 1 wherein M comprises zinc and strontium.

9) (ORIGINAL) A composition according to claim 8 having the formula  $\text{Zn}_u\text{Sr}_v\text{Ga}_2(\text{S}_x\text{Se}_y)_4\text{:Eu}$  in which u is about 0.71; v is about 0.29; x is about 0.615; and y is about 0.385.

10) (ORIGINAL) A composition comprising at least two different phosphors according to claim 1.

11) (ORIGINAL) A light emitting device comprising:

a) a light source selected from the group consisting of: light-emitting diodes and lasers, wherein said light source emits light having a wavelength of between about 360 and about 480 nanometers; and

b) a phosphor described by the formula:



in which:

M comprises one or more elements selected from the group consisting of: Be, Mg, Ca, Sr, Ba, Zn;

A comprises one or more elements selected from the group consisting of: Al, Ga, In, Y, La, and Gd;

B comprises one or more elements selected from the group consisting of: Eu, Ce, Cu, Ag, Al, Tb, Cl, Br, F, I, Mg, Pr, K, Na, and Mn,

wherein B is present in any amount between 0.0001% and about 10 % in mole percent based on the total molar weight of said composition, and wherein x and y are each independently any value between 0 and 1, subject to the proviso that the sum of x and y is equal to any number in the range of between about 0.75 and about 1.25.

12) (ORIGINAL) A light emitting device according to claim 11, wherein said phosphor emits white light when contacted with light having a wavelength of between about 360 and about 480 nanometers.

13) (ORIGINAL) A light emitting device according to claim 11 comprising a mixture of at least two different phosphors described by said formula.

14) (ORIGINAL) A light emitting device according to claim 13, wherein said mixture of phosphors emit white light when contacted with light having a wavelength of between about 360 and about 480 nanometers.

15) (ORIGINAL) A light emitting device according to claim 11 which comprises a phosphor having the formula  $Zn_uSr_vGa_2(S_xSe_y)_4:Eu$  in which u is about 0.71; v is about 0.29; x is about 0.615; and y is about 0.385.

16) (ORIGINAL) A composition of matter useful as a phosphor in light emitting diodes, which comprises a material described by the formula:



in which:

M comprises one or more elements selected from the group consisting of: Be, Mg, Ca, Sr, Ba, Zn;

A comprises one or more elements selected from the group consisting of: Al, Ga, In, Y, La, and Gd;

B comprises one or more elements selected from the group consisting of: Eu, Ce, Cu, Ag, Al, Tb, Cl, Br, F, I, Mg, Pr, K, Na, and Mn,

wherein B is present in any amount between 0.0001% and about 10 % in mole percent based on

the total molar weight of said composition, and wherein x and y are each independently any value between 0 and 1, subject to the proviso that the sum of x and y is equal to any number in the range of between about 0.75 and about 1.25.

17) (CURRENTLY AMENDED) A composition according to claim 16 wherein  $[ [ 0 \leq x \leq 1$  and  $0 \leq y \leq 1 ] ]$   $0 < x < 1$  and  $0 < y < 1$ .

18) (CURRENTLY AMENDED) A composition according to claim 16 wherein  $[ [ 0.5 \leq x \leq 1$  and  $0 \leq y \leq 0.5 ] ]$   $0.5 \leq x < 1$  and  $0 < y \leq 0.5$ .

19) (CURRENTLY AMENDED) A composition according to claim 16 wherein  $[ [ 0 \leq x \leq 0.5$  and  $0 \leq y \leq 0.5 ] ]$   $0 < x \leq 0.5$  and  $0 < y \leq 0.5$ .

20) (CURRENTLY AMENDED) A composition according to claim 16 wherein  $[ [ 0 \leq x \leq 0.5$  and  $0.5 \leq y \leq 1.0 ] ]$   $0 < x \leq 0.5$  and  $0.5 \leq y < 1.0$ .

21) (CURRENTLY AMENDED) A composition according to claim 16 wherein x is greater than ~~about~~ 0, and y is about 1.

22) (CURRENTLY AMENDED) A composition according to claim 16 wherein x is about 1, and y is greater than ~~about~~ 0.

23) (ORIGINAL) A composition according to claim 16 having the formula  $Ba_uSr_vGa_4(S_xSe_y)_7:Eu$  in which u is about 0.78, v is about 0.22, x is about 0.88; and y is about 0.12.

24) (ORIGINAL) A composition comprising at least two different phosphors according to claim 16.

25) (ORIGINAL) A light emitting device comprising:

a) a light source selected from the group consisting of: light-emitting diodes and lasers, wherein said light source emits light having a wavelength of between about 360 and about 480 nanometers; and

b) a phosphor described by the formula:



in which:

M comprises one or more elements selected from the group consisting of: Be, Mg, Ca, Sr, Ba, Zn;

A comprises one or more elements selected from the group consisting of: Al, Ga, In, Y, La, and Gd;

B comprises one or more elements selected from the group consisting of: Eu, Ce, Cu, Ag, Al, Tb, Cl, Br, F, I, Mg, Pr, K, Na, and Mn,

wherein B is present in any amount between 0.0001% and about 10 % in mole percent based on the total molar weight of said composition, and wherein x and y are each independently any value between 0 and 1, subject to the proviso that the sum of x and y is equal to any number in the range of between about 0.75 and about 1.25.


26) (ORIGINAL) A light emitting device according to claim 25, wherein said phosphor emits white light when contacted with light having a wavelength of between about 360 and about 480 nanometers.

27) (ORIGINAL) A light emitting device according to claim 25 comprising a mixture of at least two different phosphors described by said formula.

28) (ORIGINAL) A light emitting device according to claim 27, wherein said mixture of phosphors emit white light when contacted with light having a wavelength of between about 360 and about 480 nanometers.

29) (ORIGINAL) A light emitting device according to claim 25 which comprises a phosphor having the formula  $Ba_uSr_vGa_4(S_xSe_y)_7:Eu$  in which u is about 0.78, v is about 0.22, x is about 0.88; and y is about 0.12.

30) (ORIGINAL) A composition of matter useful as a phosphor in light emitting diodes, which comprises a material described by the formula:



in which:

M1 comprises an element selected from the group consisting of: Be, Mg, Ca, Sr, Ba, Zn;

M2 comprises an element selected from the group consisting of: Be, Mg, Ca, Sr, Ba, Zn

which is different from M1;

A comprises one or more elements selected from the group consisting of: Al, Ga, In, Y, La, and Gd;

B comprises one or more elements selected from the group consisting of: Eu, Ce, Cu, Ag, Al, Tb, Cl, Br, F, I, Mg, Pr, K, Na, and Mn;

wherein p can be either about 2 or about 4, and q can be either about 4 or about 7, subject to the provisos that when p is about 2, q is about 4 and when p is about 4, q is about 7;

wherein x and y are each independently any value between 0 and 1, subject to the provisos that the sum of x and y is equal to any number in the range of between about 0.75 and about 1.25, the sum of m and n is about 1; and

wherein B is present in any amount between 0.0001% and about 10 % in mole percent based on the total molar weight of said composition.

31) (CURRENTLY AMENDED) A composition according to claim 30 wherein  $[[ 0 \leq x \leq 1$   
and  $0 \leq y \leq 1 ]]$   $0 < x < 1$  and  $0 < y < 1$ .

32) (CURRENTLY AMENDED) A composition according to claim 30 wherein  $[[ 0.5 \leq x \leq 1$   
and  $0 \leq y \leq 0.5 ]]$   $0.5 \leq x < 1$  and  $0 < y \leq 0.5$ .

33) (CURRENTLY AMENDED) A composition according to claim 30 wherein  $[[ 0 \leq x \leq 0.5$   
and  $0 \leq y \leq 0.5 ]]$   $0 < x \leq 0.5$  and  $0 < y \leq 0.5$ .

34) (CURRENTLY AMENDED) A composition according to claim 30 wherein  $[[ 0 \leq x \leq 0.5$   
and  $0.5 \leq y \leq 1.0 ]]$   $0 < x \leq 0.5$  and  $0.5 \leq y < 1.0$ .



35) (CURRENTLY AMENDED) A composition according to claim 30 wherein x is greater than about 0, and y is about 1.

36) (CURRENTLY AMENDED) A composition according to claim 30 wherein x is about 1, and y is greater than about 0.

37) (ORIGINAL) A composition according to claim 30 wherein M comprises zinc and strontium.

38) (ORIGINAL) A composition comprising at least two different phosphors according to claim 30.

39) (ORIGINAL) A light emitting device comprising a phosphor according to claim 30.

40) (ORIGINAL) A light emitting device according to claim 39, wherein said phosphor emits white light when contacted with light having a wavelength of between about 360 and about 480 nanometers.

41) (ORIGINAL) A light emitting device according to claim 39 comprising a mixture of at least two different phosphors described by said formula.

42) (ORIGINAL) A light emitting device according to claim 41, wherein said mixture of phosphors emit white light when contacted with light having a wavelength of between about 360 and about 480 nanometers.